



P3 **T60*38*20** **C/P**
Material **Core Size** **Coating**
 材质 品名 涂装

C=Epoxy. P=Parylene.


Dimensions: (UNIT:mm)

Dimensions(mm)			Wt(g/set)
Epoxy Coating Dimensions(mm)			
ΦD1	ΦD2	H	137.7
60.0±1.50	38.0±1.0	20.0±0.7	
62.0max	36.0min	21.5max	



Test Conditions

AL: F=10.0KHz U=0.3V N=10Ts



Effective parameter

	Ve(mm3)	Ae(mm2)	Le(mm)
	28700	185	155

Coating


The core are coated with epoxy, flame retardant in accordance with "UL 94V-0" file number E228348. The colour is green.

Ring core data


GRADE	AL(nH)	μi	TYPE NUMBER
P3	3900±25%	≈2300	T60/38/20/P3
H5K	8100±25%	≈5000	T60/38/20/H5K
H7K	11300±25%	≈7000	T60/38/20/H7K
H10K	16000±30%	≈10000	T60/38/20/H10K

Note:


- 1: Document is the property of FUAN Inc & is not allowed to be duplicated without authorization
- 2: RoHS compliant.




P3



H5K



H7K



H10K